CTI 华测检测

240020349784

中国认可
国际互认
检测
TESTING
CNAS L1910

检测报告

Test Report

报告编号	A226087791910100102E	第 1 页 共 4 页
Report No.	A226087791910100102E	Page 1 of 4

报告抬头公司	邢台永海橡胶制品有限公司
Company Name	XINGTAI YONGHAI RUBBER PRODUCTS CO., LTD.
地　　址	邢台市内丘县家乐园商业金街 16 号
Address	NO. 16, JIALEYUAN COMMERCIAL STREET, NEIQIU COUNTY, XINGTAI CITY, HEBEI PROVINCE, CHINA

以下测试之样品及样品信息由申请者提供并确认

The following sample(s) and sample information was/were submitted and identified by/on the behalf of the client

样品名称	EPDM 橡胶密封条
Sample Name	EPDM rubber seal strip
型号	YH08
Type	YH08
样品接收日期	2026.10.10
Sample Received Date	Oct. 10, 2026
样品检测日期	2026.10.10-2026.10.20
Testing Period	Oct. 10, 2026-Oct. 20, 2026

批　　准
Approved by

林东杰
授权签字人
Approved Signatory

华测检测认证集团股份有限公司

日　　期
Date

2026.10.20
Oct. 20, 2026

No. R6B6D7284B

广东省深圳市宝安区 70 区鸿威工业园

检测报告
Test Report

检测要求
Test Requested


序号 No.	测试项目 Test Item
1	热空气老化 Air aging

检测结果：请参见后续页面。
Test Result(s): Please see the following pages.

测试样品
Tested Sample(s)

样品编号 Sample No.	样品名称 Sample Name	样品型号 Type
A2260877919101001	EPDM 橡胶密封条 EPDM rubber seal strip	YH08 YH08

样品图片
Sample Photo(s)



A2260877919101001

检测报告
Test Report

测试项目：热空气老化
Test Item: Air aging

1. 测试设备 Test Equipment

设备名称 Equipment Name	型 号 Model
烘箱 Oven	FED-720

2. 环境条件 Environmental Conditions

温度：23±2℃；湿度：50±5%RH

Temperature: 23±2℃; Humidity: 50±5%RH

3. 测试标准 Test Standard: GB/T 3512-2014

4. 测试条件

Test Condition

样品置于 100℃环境下 72h，取出，冷却后观察其外观变化。

The sample was placed at 100℃ for 72h, taken out, and its appearance was observed after cooling.

5. 测试结果

Test Result(s)


测试样品 Test Sample	测试结果 Test Results
A2260877919101001	样品无龟裂，无粉化 The sample has no crack and no pulverization.
规格值 Specification	样品无龟裂，无粉化 The sample has no crack and no pulverization.
判定 Conclusion	符合 Pass

备注：规格值由客户提供。
Remark: Specification was supplied by client.

检测报告
Test Report

测试后样品图片

Sample Photo(s) after the test



A2260877919101001

声明：

Statement:

1.检测报告无批准人签字、“专用章”及报告骑缝章无效；
This report is considered invalid without approved signature, special seal and the seal on the perforation;

2.样品及样品信息由申请者提供，申请者应对其真实性负责，CTI 未核实其真实性；
The sample(s) and sample information was/were provided by the client who should be responsible for the authenticity which CTI hasn't verified;

3.本报告检测结果仅对受测样品负责；
The result(s) shown in this report refer(s) only to the sample(s) tested;

4.未经 CTI 书面同意，不得部分复制本报告。
Without written approval of CTI, this report can't be reproduced except in full;

5.如检测报告中的英文内容与中文内容有差异，以中文为准。
In case of any discrepancy between the English version and Chinese version of the testing reports(if generated), the Chinese version shall prevail.

*** 报告结束 ***

*** End of Report ***